

DSM Coating Resins formulation No. AK06029

02/06

FUNCTION	PRODUCT	PRODUCER	PBW
Short oil alkyd	Uralac AK 424 X-60	DSM Coating Resins	16.50
Aromatic hydrocarbon	Xylene		2.00
Drier	Durham Ca 5	Elementis	0.40
Wetting agent	Nuosperse FA 601	Elementis	0.70
Anticorrosive pigment	HEUCOPHOS® ZAPP	Heubach	10.50
Iron oxide red	Bayferrox 130 M	Bayer	9.50
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	8.50
Barium sulphate	Blanc fixe micro	Sachtleben	10.00
Rheology modifier	Bentone SD-1	Elementis	0.15
<b>Grind at high speed</b>			
Short oil alkyd	Uralac AK 424 X-60	DSM Coating Resins	27.00
Drier	Durham Co 10	Elementis	0.05
Drier	Durham Zr 12	Elementis	0.45
Antiskinning agent	Exkin 2	Elementis	0.25
Aromatic hydrocarbon	Xylene		14.00
<b>Add while mixing.</b>			<b>100.00</b>
<b>SPECIFICATIONS</b>			
PVC in %			33.1
Solids in %			65.2

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.