

DSM Coating Resins formulation No. AM06021

02/06

FUNCTION	PRODUCT	PRODUCER	PBW
Phenolic modified short oil alkyd	Uralac AM 351 X-50	DSM Coating Resins	20.90
Rheology modifier	Bentone 38 paste, 10% in xylene/ethanol	Elementis	2.50
Wetting agent	Nuosperse FA 601	Elementis	0.65
Anticorrosive pigment	HEUCOPHOS® ZAPP	Heubach	12.00
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	4.00
Barium sulphate	Blanc fixe micro	Sachtleben	10.00
Iron oxide red	Bayferrox 130 M	Bayer	7.00
Add while mixing.			
Phenolic modified short oil alkyd	Uralac AM 351 X-50	DSM Coating Resins	29.20
Drier	Durham Ca 10	Elementis	0.65
Drier	Durham Co 10	Elementis	0.10
Drier	Durham Zr 12	Elementis	0.85
Antiskinning agent	Exkin 2	Elementis	0.25
Aromatic hydrocarbon	Xylene		11.90
Grind at high speed			
			100.00
SPECIFICATIONS			
PVC in %			27.0
Solids in %			59.1

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.