

Heubach formulation No. 99150

08/99

FUNCTION	PRODUCT	PRODUCER	PBW
Medium oil alkyd	Duramac 2409	McWhorter, today Eastman	20.15
Load.			
Solvent	White spirit		10.10
Rheology modifier	Bentone 34	Elementis	0.30
Solvent	Methyl alcohol		0.10
Mix until uniform paste prior to addition.			
Titanium dioxide	Ti-Pure Rutile R-902	DuPont	5.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	8.00
Magnesium silicate	Nytal 400	R.T. Vanderbilt	24.70
Grind.			
Medium oil alkyd	Duramac 2409	McWhorter, today Eastman	26.20
Solvent	White spirit		4.30
Drier	Zirconium Chem-All 12%	Mooney Chemicals	0.40
Drier	Cobalt Chem-All 12%	Mooney Chemicals	0.10
Drier	Zinc Chem-All 8%	Mooney Chemicals	0.30
Drier	Manganese Chem-All 6%	Mooney Chemicals	0.10
Antiskinning agent	Skino #1	Mooney Chemicals	0.25
Add components separately while mixing.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			18.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.