

Vianova Resins formulation No. HM 10/1 today Cytec

02/00

FUNCTION	PRODUCT	PRODUCER	PBW
Short oil alkyd	Vialkyd AF 342n/60X	Vianova Resins, today Cytec	37.60
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	8.80
Iron oxide red	Bayferrox 130	Lanxess	11.20
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	15.70
Calcium carbonate	Millicarb	Omya	8.80
Antisettling agent	Additol XL 280	Vianova Resins, today Cytec	2.30
Grind.			
Antiskinning agent	Additol XL 297	Vianova Resins, today Cytec	0.50
Lead-free drier	Octa-Soligen Drier 173	Borchers	1.40
Aromatic hydrocarbon	Xylene		13.70
Add components separately while mixing.			
			100.00
SPECIFICATIONS			
Solids in %			67.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.