

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	65,15%
------------------	--------

HEUCODUR® Yellow 152	19,60%
----------------------	--------

Iron Oxide Yellow	15,25%
-------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	64,96%
------------------	--------

HEUCODUR® Yellow 152	20,10%
----------------------	--------

Iron Oxide Yellow	14,94%
-------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390