

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	74,90%
------------------	--------

Iron Oxide Yellow	25,02%
-------------------	--------

Carbon Black	0,08%
--------------	-------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	75,25%
------------------	--------

Iron Oxide Yellow	24,67%
-------------------	--------

Carbon Black	0,08%
--------------	-------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390