

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	17,85%
------------------	--------

TICO® Yellow 622	34,78%
------------------	--------

HEUCODUR® Yellow 6R	40,12%
---------------------	--------

Iron Oxide Yellow	7,25%
-------------------	-------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	18,20%
------------------	--------

TICO® Yellow 622	34,60%
------------------	--------

HEUCODUR® Yellow 6R	40,10%
---------------------	--------

Iron Oxide Yellow	7,10%
-------------------	-------

Pigment level calculated on solid binder: 35,2%

Paint system: Air drying alkyd system based on Alkydal F48