

| PRODUCT | QUANTITY |
|---------|----------|
|---------|----------|

| | |
|------------------|--------|
| TICO® Yellow 594 | 13,50% |
|------------------|--------|

| | |
|------------------|--------|
| TICO® Yellow 622 | 46,79% |
|------------------|--------|

| | |
|----------------------|--------|
| HEUCODUR® Yellow 251 | 39,70% |
|----------------------|--------|

| | |
|--------------|-------|
| Carbon Black | 0,01% |
|--------------|-------|

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

| PRODUCT | QUANTITY |
|---------|----------|
|---------|----------|

| | |
|------------------|--------|
| TICO® Yellow 594 | 10,22% |
|------------------|--------|

| | |
|------------------|--------|
| TICO® Yellow 622 | 43,56% |
|------------------|--------|

| | |
|---------------------|--------|
| HEUCODUR® Yellow 6R | 46,22% |
|---------------------|--------|

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390

| PRODUCT | QUANTITY |
|---------|----------|
|---------|----------|

| | |
|------------------|--------|
| TICO® Yellow 594 | 10,20% |
|------------------|--------|

| | |
|------------------|--------|
| TICO® Yellow 622 | 44,80% |
|------------------|--------|

| | |
|----------------------|--------|
| HEUCODUR® Yellow 259 | 45,00% |
|----------------------|--------|

Pigment level calculated on solid binder: 35,2%

Paint system: Air drying alkyd system based on Alkydal F48