

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	2,52%
------------------	-------

TICO® Orange 640	1,50%
------------------	-------

HEUCODUR® ^{Plus} Yellow 150	75,90%
--------------------------------------	--------

HEUCODUR® Yellow G 9180	20,08%
-------------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	2,48%
------------------	-------

TICO® Orange 640	1,52%
------------------	-------

HEUCODUR® ^{Plus} Yellow 150	75,96%
--------------------------------------	--------

HEUCODUR® Yellow G 9180	20,04%
-------------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	2,61%
------------------	-------

TICO® Orange 640	1,52%
------------------	-------

HEUCODUR® ^{Plus} Yellow 150	75,80%
--------------------------------------	--------

HEUCODUR® Yellow G 9180	20,07%
-------------------------	--------

Pigment level calculated on solid binder: 31,5%

Paint system: Air drying alkyd system based on Alkydal F48