

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	18,35%
------------------	--------

TICO® Yellow 622	2,15%
------------------	-------

HEUCODUR® Yellow 152	79,50%
----------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	20,65%
------------------	--------

TICO® Yellow 622	2,55%
------------------	-------

HEUCODUR® Yellow 152	76,80%
----------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 592	12,50%
------------------	--------

HEUCODUR® <sup>Plus</sup> Yellow 150	87,00%
--------------------------------------	--------

MONOLITE® Yellow 108304	0,50%
-------------------------	-------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	10,20%
------------------	--------

TICO® Yellow 622	44,80%
------------------	--------

HEUCODUR® Yellow 259	45,00%
----------------------	--------

Pigment level calculated on solid binder: 22,1%

Paint system: water borne 2K-Polyurethane, Binder: Bayhydrol A145/Bayhydur 3100/Desmodur N 3600