

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	71,20%
------------------	--------

TICO® Yellow 622	2,10%
------------------	-------

HEUCODUR® Yellow 152	26,70%
----------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	97,59%
------------------	--------

TICO® Yellow 622	2,41%
------------------	-------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	81,20%
------------------	--------

TICO® Yellow 622	2,40%
------------------	-------

HEUCODUR® Yellow 152	16,40%
----------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	97,20%
------------------	--------

TICO® Yellow 622	2,80%
------------------	-------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390