

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	68,40%
------------------	--------

TICO® Yellow 622	3,10%
------------------	-------

HEUCODUR® Yellow 152	28,50%
----------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	96,70%
------------------	--------

TICO® Yellow 622	3,30%
------------------	-------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	88,40%
------------------	--------

TICO® Yellow 622	3,10%
------------------	-------

HEUCODUR® Yellow 152	8,50%
----------------------	-------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	98,70%
------------------	--------

TICO® Yellow 622	1,30%
------------------	-------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390