

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 588	81,25%
------------------	--------

Iron Oxide Yellow	18,75%
-------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 594	64,77%
------------------	--------

HEUCODUR® Yellow 152	20,42%
----------------------	--------

Iron Oxide Yellow	14,78%
-------------------	--------

MONOLITE® Green 600734	0,03%
------------------------	-------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390