

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	48,80%
------------------	--------

HEUCODUR® Yellow 251	51,20%
----------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	50,30%
------------------	--------

HEUCODUR® Yellow 251	49,70%
----------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390