

| PRODUCT | QUANTITY |
|---------|----------|
|---------|----------|

| | |
|------------------|-------|
| TICO® Orange 640 | 4,03% |
|------------------|-------|

| | |
|-------------------|-------|
| Iron Oxide Yellow | 5,97% |
|-------------------|-------|

| | |
|-------------------------|-------|
| HEUCODUR® Yellow G 9180 | 5,10% |
|-------------------------|-------|

| | |
|---------------------|--------|
| HEUCODUR® Yellow 3R | 19,85% |
|---------------------|--------|

| | |
|--------------------------------------|--------|
| HEUCODUR® ^{Plus} Yellow 150 | 65,05% |
|--------------------------------------|--------|

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

| PRODUCT | QUANTITY |
|---------|----------|
|---------|----------|

| | |
|------------------|-------|
| TICO® Orange 640 | 4,03% |
|------------------|-------|

| | |
|------------------|-------|
| TICO® Yellow 622 | 1,70% |
|------------------|-------|

| | |
|-------------------|-------|
| Iron Oxide Yellow | 5,97% |
|-------------------|-------|

| | |
|-------------------------|-------|
| HEUCODUR® Yellow G 9180 | 5,10% |
|-------------------------|-------|

| | |
|--------------------------------------|--------|
| HEUCODUR® ^{Plus} Yellow 150 | 63,35% |
|--------------------------------------|--------|

| | |
|---------------------|--------|
| HEUCODUR® Yellow 3R | 19,85% |
|---------------------|--------|

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390