

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	50,30%
------------------	--------

HEUCODUR® Yellow G 9180	24,60%
-------------------------	--------

HEUCODUR® Yellow 3R	15,25%
---------------------	--------

Iron Oxide Yellow	9,85%
-------------------	-------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	49,84%
------------------	--------

HEUCODUR® Yellow G 9180	29,95%
-------------------------	--------

HEUCODUR® Yellow 3R	20,19%
---------------------	--------

MONOLITE® Green 600734	0,02%
------------------------	-------

Pigment level calculated on solid binder: 25,1%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	51,20%
------------------	--------

HEUCODUR® Yellow G 9180	28,84%
-------------------------	--------

HEUCODUR® Yellow 3R	19,94%
---------------------	--------

MONOLITE® Green 600734	0,02%
------------------------	-------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	49,80%
------------------	--------

HEUCODUR® Yellow G 9180	25,10%
-------------------------	--------

HEUCODUR® Yellow 3R	14,95%
---------------------	--------

Iron Oxide Yellow	10,15%
-------------------	--------

Pigment level calculated on solid binder: 25,3%

Paint system: Air drying alkyd system based on Alkydal F48

* = Registered trademark of Heubach GmbH. Our process specific and application information are based on upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.