

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	34,90%
------------------	--------

TICO® Red 655	1,60%
---------------	-------

HEUCODUR® Yellow 6R	63,50%
---------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	37,80%
------------------	--------

TICO® Red 655	1,80%
---------------	-------

HEUCODUR® Yellow 6R	60,40%
---------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	24,80%
------------------	--------

TICO® Orange 640	14,80%
------------------	--------

HEUCODUR® Yellow 5R	60,40%
---------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390