

PRODUCT	QUANTITY
---------	----------

TICO® Orange 640	12,20%
------------------	--------

TICO® Red 655	18,00%
---------------	--------

MONOLITE® Red 312201	1,80%
----------------------	-------

HEUCODUR® Yellow 6R	68,00%
---------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems