

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 597	9,10%
------------------	-------

TICO® Orange 640	22,70%
------------------	--------

HEUCODUR® Yellow 152	68,20%
----------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 597	10,10%
------------------	--------

TICO® Orange 640	23,10%
------------------	--------

HEUCODUR® Yellow 152	66,80%
----------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390