

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	29,10%
------------------	--------

TICO® Orange 640	40,05%
------------------	--------

TICO® Red 655	2,35%
---------------	-------

HEUCODUR® Yellow 6R	28,50%
---------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	29,45%
------------------	--------

TICO® Orange 640	39,50%
------------------	--------

TICO® Red 655	2,40%
---------------	-------

HEUCODUR® Yellow 6R	28,65%
---------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390