

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	34,00%
------------------	--------

TICO® Orange 640	25,00%
------------------	--------

TICO® Red 655	2,00%
---------------	-------

HEUCODUR® Yellow 6R	34,00%
---------------------	--------

Iron Oxide Red	5,00%
----------------	-------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Yellow 622	37,10%
------------------	--------

TICO® Orange 640	26,10%
------------------	--------

TICO® Red 655	2,28%
---------------	-------

HEUCODUR® Yellow 6R	29,80%
---------------------	--------

Iron Oxide Red	4,72%
----------------	-------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390