

PRODUCT	QUANTITY
---------	----------

TICO® Orange 640	19,20%
------------------	--------

TICO® Yellow 622	19,60%
------------------	--------

HEUCODUR® Yellow 255	61,20%
----------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Orange 640	19,70%
------------------	--------

TICO® Yellow 622	19,80%
------------------	--------

HEUCODUR® Yellow 255	60,50%
----------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390