

PRODUCT	QUANTITY
---------	----------

TICO® Red 655	9,05%
---------------	-------

HEUCODUR®Plus Yellow 150	56,25%
--------------------------	--------

HEUCODUR® Yellow 3R	34,70%
---------------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Red 655	8,97%
---------------	-------

HEUCODUR®Plus Yellow 150	56,10%
--------------------------	--------

HEUCODUR® Yellow 3R	34,93%
---------------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390