

PRODUCT	QUANTITY
---------	----------

TICO® Red 655	70,00%
---------------	--------

HEUCODUR® Yellow 6R	10,00%
---------------------	--------

MONOLITE® Red 312201	10,00%
----------------------	--------

Iron Oxide Red	10,00%
----------------	--------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems