

PRODUCT	QUANTITY
---------	----------

TICO® Red 655	34,00%
---------------	--------

HEUCODUR® Yellow 6R	40,00%
---------------------	--------

HEUCODUR® Yellow 255	10,00%
----------------------	--------

MONOLITE® Red 312201	13,00%
----------------------	--------

Pigment Violet 19	3,00%
-------------------	-------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems