

PRODUCT	QUANTITY
---------	----------

TICO® Red 655	19,00%
---------------	--------

HEUCODUR® Yellow 6R	53,00%
---------------------	--------

MONOLITE® Red 312201	20,00%
----------------------	--------

Pigment Violet 19	8,00%
-------------------	-------

Pigment level calculated on solid binder: 23,7%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems