

PRODUCT	QUANTITY
---------	----------

TICO® Red 655	31,10%
---------------	--------

HEUCODUR® Yellow 255	52,10%
----------------------	--------

Iron Oxide Red	16,80%
----------------	--------

Pigment level calculated on solid binder: 23,6%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Red 655	31,10%
---------------	--------

HEUCODUR® Yellow 255	52,20%
----------------------	--------

Iron Oxide Red	16,70%
----------------	--------

Pigment level calculated on solid binder: 26,9%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390