

PRODUCT	QUANTITY
---------	----------

TICO® Red 655	71,40%
---------------	--------

HEUCODUR® Yellow 6R	28,60%
---------------------	--------

Pigment level calculated on solid binder: 23,6%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Red 642	16,73%
---------------	--------

TICO® Red 655	60,50%
---------------	--------

HEUCODUR® Yellow 6R	22,77%
---------------------	--------

Pigment level calculated on solid binder: 23,6%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Red 642	22,40%
---------------	--------

TICO® Red 655	77,60%
---------------	--------

Pigment level calculated on solid binder: 23,6%

Paint system: alkyd melamine resin based on Alkydal F300/Maprenal MF650 and other stoving enamel systems

PRODUCT	QUANTITY
---------	----------

TICO® Red 655	70,60%
---------------	--------

HEUCODUR® Yellow 6R	29,40%
---------------------	--------

Pigment level calculated on solid binder: 23,6%

Paint system: 2K-Polyurethane, solvent based on Desmophen A365/Desmodur N3390