

PRODUCT DESCRIPTION

HEUCOSPERSE - I OS 1271 E is a solvent free Pigment Orange 5 dispersion based on a styrene acrylic resin (ammonia stabilized). Easily stir-in dinitranilinorange dispersion suitable for various waterbased inks. It is especially designed for printing kraft paper, paper & paperboard ink systems.

Colour Index Name Pigment Orange 5

C.I. Constitution No. 12075

Chemical Type β -Naphthol

CAS No. 3468-63-1

Pigment Content [%] 35

PHYSICAL DATA

Appearance orange liquid

Specific Gravity [g/cm³] 1,14 AA10/PPB/014

pH 8,0 - 9,0 AA10/PPB/002

Total Solids [%] 40 - 44 AA10/PPB/001

COLORISTIC SPECIFICATION

Tinting Strength [%] 95,0 - 105,0

DE 0 to +1,5 [CIELAB]

DL -1 to +1 [CIELAB]

Da -1 to +1 [CIELAB]

Db -1 to +1 [CIELAB]

DC -1 to +1 [CIELAB]

DH -1 to +1 [CIELAB]

FULL TONE



FASTNESS PROPERTIES ¹⁾

Light	Full Tone	1:1 TiO ₂	1/3 STD
	6	5	5

Acid 5

Alkali 5

APPLICATION PROFILE

Water based Inks main application

Flexographic Inks main application

Gravure Inks main application

STANDARD PACKAGING

- 20kg, 25kg, resp. 200kg Plastic Drums
- 600kg and 1.000kg Container

- Details concerning other types of packaging are available on request

WARRANTY

Warranty after delivery [months] 12

1) The performance data shown below is taken from the pigment suppliers' literature. The information contained herein is based on technical data believed to be reliable and is expressed without liability or warranty.

® = Registered trademark of Heubach GmbH. Our product specifications and application information is based on our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and us.