

# HEUCOTINT W 20 IPT PLUS

Tinting System



COMPETENCE IN COLOR

	HEUCOTINT W	Pigment	Index		Lightfastness		Weatherfastness		Specific Gravity [g/ml] approx.	Pigment Content [%] approx.	Silicate
					Full Tone	Red.	Full Tone	Red.			
	50062 White	Titanium Dioxide	P.W.6	Inorganic	8	8	5	5	2,20	72	+
	50110 Inorganic Black	Iron Oxide Black	P.Bk.11	Inorganic	8	8	5	5	1,89	57	+
	50070 High Concentrated Black	Carbon Black	P.Bk.7	Inorganic	8	8	5	5	1,25	42	-
	50426 Yellow Oxide	Iron Oxide Yellow	P.Y.42	Inorganic	8	8	5	5	1,82	60	+
	51842 Inorganic Bright Yellow	Bismuth Vanadate	P.Y.184	Inorganic	8	8	5	5	2,23	67	o
	50740 High Concentrated Yellow	Monoazo Yellow	P.Y.74	Organic	7-8	6-7	4-5	4	1,16	47	-
	50429 Inorganic Orange Oxide	Iron Oxide Yellow	P.Y.42	Inorganic	8	8	5	5	1,90	63	+
	50744 Durable Organic Orange	Monoazo Orange	P.O.74	Organic	7-8	6-7	4	3-4	1,17	42	-
	51014 Red Oxide Blue Shade	Iron Oxide Red	P.R.101	Inorganic	8	8	5	5	2,04	65	+
	51015 Red Oxide Yellow Shade	Iron Oxide Red	P.R.101	Inorganic	8	8	5	5	2,10	65	+
	51120 High Concentrated Red	Naphthol AS	P.R.112	Oorganic	7-8	6	4-5	3-4	1,18	47	-
	51220 Magenta	Quinacridone Magenta	P.R.122	Organic	7-8	7-8	4-5	4	1,11	28	-
	51680 Durable Organic Red	Anthanthrone Red	P.R.168	Organic	8	8	5	5	1,25	38	-
	50230 High Concentrated Violet	Dioxazine Violet	P.V.23	Organic	8	7-8	4-5	4	1,25	30	-
	50280 Inorganic Blue	Cobalt Blue	P.B.28	Inorganic	8	8	5	5	1,89	58	+
	50290 Inorganic Bright Blue	Ultramarine Blue	P.B.29	Inorganic	8	8	5	5	1,42	54	+
	51530 High Concentrated Blue	Phthalocyanine Blue	P.B.15:3	Organic	8	8	5	5	1,27	46	-
	50170 Inorganic Green	Chromium Oxide Green	P.G.17	Inorganic	8	8	5	5	2,28	73	+
	50501 Inorganic Bright Green	Cobalt Green	P.G.50	Inorganic	8	8	5	5	2,31	70	+
	50071 High Concentrated Green	Phthalocyanine Green	P.G.7	Organic	8	8	5	5	1,37	50	-

These information are guidance figures only, testing in customer products is recommended. Light fastness is measured on a scale from 1 to 8, where 1 = severe change, 8 = no change. Weather fastness is measured on a scale from 1 to 5, where 1 = severe change, 5 = no change. Silicate: + = recommended, o= limited suitability, - = not recommended. The colors above have been generated electronically and should therefore not be used for comparison purposes. The brochure colors are meant to give a first impression of the colorant shade.

® = Registered trademark of Heubach GmbH. Our product specifications and application information is based on our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and us.