

PRODUCT DESCRIPTION	
The TICO® product line represents a novel approach to pigment preparations made by a proprietary co-finishing process to attach the organic high performance pigments to the surface of the inorganic titanium yellows. TICO® Red 645 is a medium shade red with excellent opacity and high tinctorial strength. Due to its excellent fastness properties it can be used for highly durable applications.	
Chemical Type	hybrid pigment
Color Index	-
Hue Angle at Full Shade	30,2

APPLICATION PROFILE	
Air drying Alkyds	potential use
Baking enamel	potential use
Acid curing systems	potential use
Amine curing systems	potential use
Isocyanate curing systems	potential use
Water borne paints	potential use
OEM Automotive Refinish	potential use
Coil coatings	recommended

REGULATIONS	
This product is not approved for food contact use in Europe.	
USA (FDA) 21 CFR § 178.3297	not listed
Toys Europe EN 71-3	not compliant
Toys USA ASTM F 963-03	not compliant
CONEG, EC 94/62	compliant
ROHS, 2002/95/E, 2005/618/EC	compliant
End of Life Vehicles, 2000/53/EC, 2002/525/EC	compliant

CHEMICAL INVENTORY LISTING STATUS	
All ingredients of TICO® Red 645 are listed in the following national chemical inventories:	
EINECS [Europe], TSCA [USA], MITI [Japan], IECS [China].	

FULL TONE	REDUCTION
	

FASTNESS PROPERTIES	
Acid <sup>7)</sup>	5
Alkali <sup>7)</sup>	5
Overpainting [AM (160°C/30 min)] <sup>6)</sup>	5
Water <sup>5)</sup>	5
Butanol <sup>5)</sup>	4 - 5
Butylacetate <sup>5)</sup>	4 - 5
Xylene <sup>5)</sup>	4 - 5
MEK <sup>5)</sup>	4 - 5
White Spirit <sup>5)</sup>	5
DOP <sup>5)</sup>	4 - 5
Heat Resistance [°C] <sup>8)</sup>	250
Light Fastness [Full Shade] <sup>3)</sup>	8
Weather Fastness [Full Shade] <sup>4)</sup>	5
Weather Fastness [1:3 Reduction] <sup>4)</sup>	4 - 5

PHYSICAL DATA	
Appearance	red powder
Density [g/cm <sup>3</sup> ]	2,9
Bulk Volume [cm <sup>3</sup> /g]	1,8
Average Particle Size [µm]	0,4
Oil Absorption [g/100g]	15
Specific Surface [m <sup>2</sup> /g]	5,8
pH	7 - 9

STANDARD PACKAGING
- 15 kg Paper Bags - Different types of packaging are available on request

- 1) Hue angle at full shade according to German Standard 6174.
- 2) Ratio of pigment to titanium dioxide in order to achieve 1/3 ISD according to German Standard 53235.
- 3) Light fastness was tested in an alkyd/melamine system. Assessment with Blue Wool Scale according to DIN 54003. Rating: 1=very poor, 8=outstanding.
- 4) Weathering fastness was tested in a waterborne acrylic resin system. Assessment with Grey Scale according to DIN 54001 after 2000h accelerated weathering (Arc Xenontest acc. to DIN EN ISO 11341-1-A, 1998). Rating: 1=poor, 5=very good.
- 5) Pigments were dipped into solvent. Assessment with Grey Scale according to DIN 54002. Rating: 1=severe, 5=none.
- 6) Assessment of bleeding of a white NC-topcoat using the Grey Scale according to DIN 54002. Rating: 1=severe, 5=none.
- 7) Pigments were dipped into hydrochloric acid or sodium carbonate solutions of varying concentrations. Rating: 1=poor, 5=excellent.
- 8) Pigments were tested in an alkyd / melamine system with 30 minutes baking time. Temperature range 140°C to 200°C.

® = Registered trademark of Heubach GmbH. Our product specifications and application information is based on our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and us.